

Polymer Works, Hope Street
Dudley, West Midlands DY2 8RS

t: 01384 252555

f: 01384 252373

e: technical@advancedseals.co.uk



<http://www.advancedseals.co.uk>

Specification Sheet / 01

KTAL03 Foil Class O to BS476 6 & 7 1987



ISO9001, ISO14001, ISO45001
Certificate Ref: 11739

Property	Value
Release liner grade	Glassine
Release liner colour	White
Release liner Thickness	60 Micron
Adhesive type	Acrylic
Adhesive thickness	30 micron
Foil thickness	30 micron

Peel adhesion to steel	Loop tack	Release from liner	Temperature range	Shear
800 n/m	500 n/m	10 n/m	-40 °c to 120 °c	200 hours

Change Control Date	Change
28/10/16	Created



The above figures are average values.
We recommend that you examine any material you select to ensure its suitability for your application.
Tolerance(s) applied in accordance with ASG specification No W1007 (<https://bit.ly/3nKm6Hj>) unless otherwise stated.
Our standard terms and conditions of trading (<https://bit.ly/3b3mThw>) apply at all times.

